

CLIPPEDIMAGE= JP407207551A

PAT-NO: JP407207551A

DOCUMENT-IDENTIFIER: JP 07207551 A

TITLE: PRODUCTION OF KNITTED FABRIC HAVING HIGH ELASTIC PROPERTY

PUBN-DATE: August 8, 1995

INVENTOR-INFORMATION:

NAME

NISHIJIMA, SEIICHI

TAKAMI, MINORU

FUJIMOTO, YASUHIRO

ASSIGNEE-INFORMATION:

NAME

UNITIKA LTD

COUNTRY

N/A

APPL-NO: JP05352138

APPL-DATE: December 31, 1993

INT-CL (IPC): D04B001/16;D06C007/00 ;D01F006/62 ;D01F006/62

ABSTRACT:

PURPOSE: To obtain a high-density knitted fabric having soft touch feeling of surface and excellent stretchability.

CONSTITUTION: Yarn A composed of thermally extensible polyester-based fiber is prepared. The thermally extensible polyester-based fiber is preferably produced by thermally stretching highly oriented undrawn yarn of polyester which has a main repeating unit composed of ethylene terephthalate and 15-45% structure integration parameter at a temperature $\geq 25^{\circ}\text{C}$ higher than the glass transition temperature and heat-treating at a temperature $25-90^{\circ}\text{C}$ lower than the melting point. Besides, yarn B comprising

thermally shrinkable
polyester fiber is prepared. Knitting is carried out in
such a way that the
yarn A is positioned at the outside of knitted stitches by
plaiting knitting
and the yarn B is arranged inside the knitted stitches.
The knitted fabric is
dyed, processed and heat-treated during the dyeing and
processing.

COPYRIGHT: (C)1995,JPO